



## RM0590 Retarder MG/Printgen MG

Mix 1-5% of Retarder MG in to ink to help extend the open time and keep the product from clogging in the screen. 35% humidity or above in your shop will also help extend the open time of waterbase inks.

## WB1011 Softener MG/Softener XA-1

Softener MG is a silicone softener that helps the hand of a print. You can also blend in to waterbase inks at 10% to act as a foil release agent. Softener MG at 20% mixed in to water also makes an excellent cleaning solution for cleaning screens and mixing utensils.

## RM0461 Fixer WF-F

Use Fixer WF-F at 2-3% to help with wash fastness. Fixer WF-F also lowers the cure temperature to 120°C. The pot life of the ink is roughly 24 hours once mixed. This fixer **DOES NOT** meet all RSL's (Restricted Substance List) of all major brands.

## RM0480 Fixer WF-N

Use Fixer WF-N at 1-4% to help with wash fastness. Fixer WF-N lowers the cure temperature to 150°C. There is no limited pot life with Fixer WF-N. This fixer **DOES** meet All RSL's (Restricted Substance List) of all major brands.

## RM0680 Carrier B/Thickener B

Use Carrier B/Thickener B at 0.25-1% to raise the viscosity and help hold your dot for halftone printing. Be sure to use a high speed mixer when adding this product into your ink. Creates a short bodied ink.

## RM0456 Discharge Agent

Add between 1-10% of discharge agent to activate discharge inks. Recommended use is typically 6%.

**Note:** Adding discharge agent to water and allowing to dissolve before adding into finished inks results in a more thorough mix.